

EZ - TIG AlMg3

CLASSIFICATION

EN ISO 18723	AWS / ASME SFA-5.10	W. Nr.
S Al 5754 / Al Mg3	ER5754	3.3536

DESCRIPTION AND APPLICATION

Aluminum solid rod for TIG welding alloyed with 3% of magnesium. Rod is intended for welding Al-Mg alloys which contains < 3% magnesium. Weld metal has elevated tensile strength and corrosion resistance.

MECHANICAL PROPERTIES OF THE ALL-WELD METAL

R _{p0,2} N/mm ²	R _m N/mm ²	A ₅ %
110	230	> 23

APPROXIMATE CHEMICAL COMPOSITION OF THE ROD

	Al	Mg	Mn	Cr	Si	Fe
%	bal.	3,0	0,2	0,01	0,05	0,12

SHIELDING GAS

l1 (Ar)

PACKAGING

Rod diameter mm	Rod length mm	Weight of packaging kg
1,2; 1,6; 2,0; 2,4; 3,2; 4,0	1000	5



Marking: 3.3536 / 5754